

Polar®

Choice Clear

Polar® Choice Clear is the ideal choice for a printable monomeric PVC film. Available with a gloss finish and permanent or removable adhesive, Polar® Choice Clear maximises adhesive performance on a wide variety of substrates.

Polar® Choice Clear is outdoor durable for up to 3 years and is ideal for signage and general advertising applications, including windows, POP displays, stickers and decals.

- IDEAL FOR INDOOR & OUTDOOR GENERAL SIGNAGE & DISPLAY
- WINDOW GRAPHICS
- SUITABLE FOR MANY APPLICATIONS

Product Codes:

PDE - Polar Choice Clear Gloss P

CRCG - Polar Choice Clear Gloss R

Polar Choice
Clear Gloss P

80 | **70**
micron

Clear
Monomeric
PVC

☐ Gloss



(Eco)Solvent
Latex
UV



Permanent or Removable
Acrylic Solvent
Adhesive



Widths up to 1524mm



3 YEARS DURABILITY
INTERIOR & EXTERIOR

THE CHOICE FOR MONOMERIC PVC



APPLICATIONS

GENERAL SIGNAGE
WINDOW GRAPHICS
EXHIBITION GRAPHICS
POS DISPLAY



DRYTAC®

ADHESIVE SCIENCE

www.drytac.com

Polar®

Choice Clear Gloss P

Polar® Choice Clear P is an 80µ (3.2 mil) gloss clear monomeric PVC film, coated on one side with a permanent, pressure sensitive clear solvent acrylic adhesive that is protected by a 140gsm 2 side PE coated release liner. Suitable for interior and exterior use (up to 3 years).

- IDEAL FOR GENERAL SIGNAGE & GRAPHIC PROMOTIONS
- SUITABLE FOR INTERIOR AND EXTERIOR USE
- CAN BE APPLIED TO MANY SMOOTH SURFACES

INSTALLATION RECOMMENDATION

The surface must be clean and smooth and free of defects before application.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2020 Drytac Corporation. E&OE.
All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Clear Gloss Monomeric PVC
Adhesive	Clear Permanent Solvent Acrylic (Pressure Sensitive)
Release Liner	140gsm 2 side PE Coated Release Paper

PRODUCT CHARACTERISTIC

Film Thickness	3.2 mil (80µ) 4.2 mil (105µ)
Adhesive Layer	1 mil (25µ) (105µ)
Outdoor Durability	3 Years
Fire Rating (EN 13501-1)	Class C-s1, d0
Application Temperature	>41°F (5°C)
Service Temperature Range	-4°F to 149°F (-20°C to 65°C)
Shelf Life	2 years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

OVERLAMINATE RECOMMENDATIONS

When using Polar® Choice, an overlaminate can be used for maximum life expectancy. Products recommended for use with Polar® Choice are Drytac's Dynamic™, Interlam™ or Protac™ overlaminates.

DRYTAC®
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5401-B Eubank Road,
Sandston,
Virginia, 23150,
USA
customerservice@drytac.com
Tel: +1 800.280.6013

www.drytac.com

Polar®

Choice Clear Gloss R

Polar® Choice Clear R is an 70µ (2.8 mil) gloss clear monomeric PVC film, coated on one side with a removable, pressure sensitive clear solvent acrylic adhesive that is protected by a 140gsm 2 side PE coated release liner. Suitable for interior and exterior use (up to 3 years).

- IDEAL FOR GENERAL SIGNAGE & GRAPHIC PROMOTIONS
- SUITABLE FOR INTERIOR AND EXTERIOR USE
- CAN BE APPLIED TO MANY SMOOTH SURFACES

INSTALLATION RECOMMENDATION

The surface must be clean and smooth and free of defects before application.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2020 Drytac Corporation. E&OE.
All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Clear Gloss Monomeric PVC
Adhesive	Clear Removable Solvent Acrylic (Pressure Sensitive)
Release Liner	140gsm 2 side PE Coated Release Paper

PRODUCT CHARACTERISTIC

Film Thickness	2.8 mil (70µ) 3.8 mil (95µ)
Adhesive Layer	1 mil (25µ) (95µ)
Outdoor Durability	3 Years
Fire Rating (EN 13501-1)	Class B
Application Temperature	>41°F (5°C)
Service Temperature Range	-4°F to 149°F (-20°C to 65°C)
Shelf Life	2 years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

OVERLAMINATE RECOMMENDATIONS

When using Polar® Choice, an overlaminate can be used for maximum life expectancy. Products recommended for use with Polar® Choice are Drytac's Dynamic™, Interlam™ or Protac™ overlaminates.

DRYTAC®
ADHESIVE SCIENCE

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5401-B Eubank Road,
Sandston,
Virginia, 23150,
USA
customerservice@drytac.com
Tel: +1 800.280.6013

www.drytac.com